

**PROBOND 62-DCP**  
**Damp Concrete Primer**

**Technical Data**

**DESCRIPTION:** Probond 62-DCP Primer is a two-component epoxy designed for use with Parker Protech and Chemline Industrial Systems where cold and damp conditions exist.

**RECOMMENDED USES:** To prime and prepare concrete for Parker topcoats where cold and damp conditions exist. Warehouses, cooler floors and areas exposed to high moisture. Prime surfaces that have been wet prepped.

**CHEMICAL RESISTANCE:** Determined by Parker topcoat applied.

**PHYSICAL CHARACTERISTICS:** Superior bonding properties under adversely damp conditions

**FINISH:** Gloss

**VOLUME SOLIDS:** 100%

**FLASH POINT:** Not applicable

**SUGGESTED DRY FILM THICKNESS:** 8 mils

**EXPECTED COVERAGE:** 120 sq. ft. per unit at recommended DFT


**COLOR:** Amber

**PACKAGING:** 1 unit = 1 quart can (short filled) Part A, Activator  
1 gallon can (short filled) Part B, Base  
1 unit = .63 gallon

**SHIPPING WEIGHT:** 1 unit = 8 lbs.

All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know-how, at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendation, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.

**PARKER COATINGS, INC. - 2451 W. MASON ST. - GREEN BAY, WI 54303**  
**920-494-9676 800-236-9676**



## PROBOND 62-DCP

## Application Data

**SURFACE PREPARATION:** NEW CONCRETE must have a minimum of 28 days cure, and no curing agents shall be used. Remove oil, dirt, grease or other foreign materials and contaminants. A good bonding tooth is necessary. To provide a bonding tooth, prepare the surface by sandblasting, scarifying, shot blasting or acid etching. OLD CONCRETE, remove all powdery and weak concrete. METAL SURFACES should be cleaned by solvent degreasing followed by abrasive blasting to near white metal SSPC-10-70 Or NACE #2 with a 4 mil minimum anchor pattern "tooth".

**MIXING:** Pour Part A into Part B. Mix thoroughly for 2-4 minutes.

**POT LIFE:** 25-30 minutes at 70 degrees. F. and 50% R.H.

**APPLICATION TEMPERATURE:** Do not apply when the surface temperature is below 32 degrees. F.

**CURE TIME:** When used as a primer for aggregate filled, trowel applied overlays: 1-2 hours at 70 degrees. F., 50% R.H. If more than two(2) hours is expected to pass before overlaying, lightly broadcast large section just prior to overlay application. For thin film overlays, contact Parker Technical Department for specific instructions.

**APPLICATION:** Apply by brush or 3/8" or 1/2" nap roller.

**CLEAN UP:** Probond 62-DCP cured or hardened, will stick to practically everything and is almost impossible to remove. Clean your tools immediately with P35T Thinner or hot soapy water.

**CAUTION:** It is recommended that the personnel observe good personal hygiene. Certain personnel may be sensitive to various types of resins which may cause dermatitis. Do not use in confined space or closed area without adequate ventilation. This product may be irritating to eyes and skin. Avoid contact with liquid components A and B and keep mortar from touching tool handles and clothes. Use coveralls, goggles, rubber gloves or protective cream. Always wash thoroughly with soap and warm water after use. Should accidental eye contact occur, wash thoroughly with water and consult a physician immediately. U.S. Department of Labor approved material data sheet is available.

**LIMITED WARRANTY:** The Manufacturer warrants this product to be free from defects in material and workmanship under normal use and service for a period of one year of the date of purchase. The Manufacturer's sole liability shall be limited to replacing this product if, within one year of the date of purchase, it is shown to be defective. THIS WARRANTY IS EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS OF PURPOSE. THE MANUFACTURER SHALL NOT BE LIABLE FOR INDIRECT, INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES OF ANY KIND. This warranty shall not be extended, altered or varied except by a written instrument signed by the Manufacturer.