

PROBOND 26-CP
Concrete Primer

Technical Data

DESCRIPTION: Probond 26-CP is a two-component polyamide-activated epoxy formulated to provide maximum adhesion to concrete, wood and steel. Probond 26-CP also exhibits superior qualities for interfacial adhesion with catalyzed and moisture cured urethanes along with single and two-component epoxy topcoats.

RECOMMENDED USES: For penetrating bond coat where moisture barriers are needed for urethane and epoxy thin film topcoats.

CHEMICAL RESISTANCE: Dependent upon Parker topcoat applied.

FINISH: Gloss

VOLUME SOLIDS: 40.0%

FLASH POINT: Part A : 79 degrees. F. Seta Flash
Part B : 60 degrees. F. Seta Flash

SUGGESTED DRY FILM THICKNESS: 4-6 mils

EXPECTED COVERAGE: 320-214 sq. ft. per unit at suggested dry film thickness

COLORS: Various


PACKAGING: 1 unit = 1 gallon can (short filled) Part A, Activator
1 gallon can (full) Part B, Base
1 unit = 1.91 gallons

SHIPPING WEIGHT: 1 unit = 18 lbs.

USDA APPROVAL: Yes

All technical advice, recommendations and services are rendered by the Seller gratis. They are based on technical data which the Seller believes to be reliable, and are intended for use by persons having skill and know-how, at their own discretion and risk. Seller assumes no responsibility for results obtained or damages incurred from their use by Buyer in whole or in part. Such recommendation, technical advice or services are not to be taken as a license to operate under or intended to suggest infringement of any existing patent.

PARKER COATINGS, INC. - 2451 W. MASON ST. - GREEN BAY, WI 54303
920-494-9676 800-236-9676



PROBOND 26-CP

Application Data

SURFACE PREPARATION: NEW CONCRETE - Remove all dust, dirt, grease and other foreign materials. For maximum adhesion, acid etching may be required. Surface must be thoroughly dry before application. METAL SURFACES should be cleaned by solvent degreasing. WOOD should be free from dust, dirt, grease and other foreign materials. TILE - remove any wax or topcoat and clean thoroughly, allowing to dry before application.

MIXING: Mix Part A with Part B for approximately five (5) minutes. Allow to sit for approximately 10 minutes for induction time before application.

POT LIFE: 1 hour at 70 degrees. F. and 50% R.H. after induction time.

APPLICATION TEMPERATURE: Do not apply when temperature is below 50 degrees. F. Temperature of coating and substrate should be 60-70 degrees. F.

CURE TIME: Recoat: 2-4 hours at 70-75 degrees. F., 50% R.H. 4-8 hours if temperature is below 65 degrees F. If recoat time exceeds 8 hours, reprime using Probond 26-CP.

APPLICATION: Apply brush, roller or spray. Use Binks #18 Spray Gun, 66 tip, 66PB nozzle or equal. Airless Spray: Use of spray tips with an .015-.109 orifice is suggested. Back roll for maximum substrate penetration when spray applied.

CLEAN UP: Clean all spills and tools with P32T Thinner or hot soapy water.

CAUTION: It is recommended that the personnel observe good personal hygiene. Certain personnel may be sensitive to various types of resins which may cause dermatitis. Do not use in confined space or closed area without adequate ventilation. This product may be irritating to eyes and skin. Avoid contact with liquid components A and B and keep mortar from touching tool handles and clothes. Use coveralls, goggles, rubber gloves or protective cream. Always wash thoroughly with soap and warm water after use. Should accidental eye contact occur, wash thoroughly with water and consult a physician immediately. U.S. Department of Labor approved material data sheet is available.

LIMITED WARRANTY: The Manufacturer warrants this product to be free from defects in material and workmanship under normal use and service for a period of one year of the date of purchase. The Manufacturer's sole liability shall be limited to replacing this product if, within one year of the date of purchase, it is shown to be defective. THIS WARRANTY IS EXPRESSLY IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING THE WARRANTIES OF MERCHANTABILITY AND FITNESS OF PURPOSE. THE MANUFACTURER SHALL NOT BE LIABLE FOR INDIRECT, INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES OF ANY KIND. This warranty shall not be extended, altered or varied except by a written instrument signed by the Manufacturer.

